



CF kunststofprofielen
Member of C.F. Kunststoffen B.V.

Postadres
Postbus 1
NL 7783 ZG
Gramsbergen

Adres
Doorbraakweg 45
NL 7783 DC
Gramsbergen

Telefoon
+31(0)524 56 17 08
Fax
+31(0)524 56 14 39

E-mail
info@cf-kunststofprofielen.nl
Internet
www.cf-kunststofprofielen.nl

Technical Datasheet raw material supplier

CF code: PB12343

Description: PlastBlend wit Granulate

Application: Plastblends are high end modified PVC compounds, with excellent outdoor behaviour, high heat resistance (vicat) and superior fire resistance properties.

Properties	Value	Test method
Density	1,44	ISO 1183 (gr/cm ³)
Softening point (VICAT)	95	ISO 306 (5kg-Celsius)
IZOD	>12	ISO 179 (Kj/m ² ; +23C)
Tensile strength at yield	44	ISO 527-I (N/mm ²)
Tensile strength at break	42	ISO 527-I (N/mm ²)
Elongaton at break	160%	ISO 527-I
Elongation at yield	4,1%	ISO 527-I
Elasticity module at bending	3700	ISO 178

The data given above are typical results from tests done in the laboratory. They do not form the whole or part of a specification. Since the conditions under which the products may be used are beyond our control, recommendations are made without guarantee and customers should ensure that materials supplied are satisfactory for their requirements.

September 2019

K.v.K. Oost-NL
05040934

BTW
NL009330008B01

IBAN
NL15 RABO 0322 7240 23

BIC Swift
RABONL2U

Op al onze transacties en aanbiedingen zijn onze algemene voorwaarden, gedeponeerd bij de K.v.K. Oost-Nederland, van toepassing.
Een exemplaar van deze voorwaarden wordt u op aanvraag toegezonden.